

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ :
B32B 31/30, 15/08, B29C 39/18

A1

(11) International Publication Number: WO 98/39160

(43) International Publication Date: 11 September 1998 (11.09.98)

(21) International Application Number: PCT/NL98/00051

(22) International Filing Date: 23 January 1998 (23.01.98)

(30) Priority Data:

1005066	23 January 1997 (23.01.97)	NL
1005304	18 February 1997 (18.02.97)	NL

(71) Applicant (for all designated States except US): HOOGOVENS
STAAL B.V. [NL/NL]; P.O. Box 10000, NL-1970 CA
Umuiden (NL).


(72) Inventor; and

(75) Inventor/Applicant (for US only): BEENTJES, Petrus, Cor-
nelis, Jozef [NL/NL]; Cieweg 43, NL-1902 AA, Castricum
(NL).(74) Agent: HERMAN DE GROOT, Johan, Willem; Hoogovens
Corporate Services B.V., P.O. Box 10000, NL-1970 CA
Umuiden (NL).(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR,
BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE,
GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ,
LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW,
MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO
patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT,
LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI,
CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.
In English translation (filed in Dutch).

BEST AVAILABLE COPY

(54) Title: METHOD AND APPARATUS FOR STRIP-COATING A METALLIC STRIP-SHAPED SUBSTRATE WITH A PLASTIC
BAND AND STRIP THUS OBTAINED

(57) Abstract

Method for strip-coating a metallic strip-shaped substrate (1) with a band (3) of plastic comprising the stages: (i) in-situ casting of a plastic band; (ii) leading the plastic band around a cooling roll (5, 5a); (iii) leading away the plastic band until the plastic band production is underway and stabilized; (iv) bringing the plastic band up to speed and heating the substrate to a temperature of the substrate close to the softening temperature of the part of the plastic band facing the substrate; (v) pressing the plastic band onto the substrate and where applicable breaking off the plastic band and stopping it being led away; (vi) coating the substrate (1) with the plastic band (3) at high speed.